



## Product description

Silane grafted compound, moisture curable by addition of a catalyst masterbatch (Sioplas<sup>®</sup> method), containing a fire retardant system that contributes to give the cable self-extinguish properties without halogenidric acids evolution, toxic and corrosive gases and dark smoke emission. This material complies with RoHS requirements.

Application: W&C sheathing

## Standard complying

EN 50363-6 EM8 and EM10; IEC 60092 SHF2; VDE 0266 HXM1; VDE 0207 HM3; BS 7655 LRS1, SW3 and SW4.

Burning behavior to be assessed accordingly to performances required by specific cable construction

## Availability

Africa & Middle East, Asia Pacific, Europe, Latin America

Verify commercial availability and registration status in each country with local sales representative

Typical properties <sup>(1)</sup>	nominal value	unit	test method
<b>Physical</b>			
Density at 23°C	1.59	g/cm <sup>3</sup>	ASTM D792
Melt Flow Index, 190°C/21.6 kg <sup>(2)</sup>	8.0	g/10'	Internal method
Water absorption, 168 hs at 70°C	3.79	mg/cm <sup>2</sup>	EN 60811
Water absorption, 24 hs at 100°C	3.33	mg/cm <sup>2</sup>	EN 60811
Hardness, Shore D	38		ISO 868
<b>Mechanical</b>			
Tensile Strength at break	11.0	MPa	EN 60811
Tensile Elongation at break	180	%	
<b>Thermal</b>			
Hot Set Test at 200°C, 20 N/cm <sup>2</sup>			
elongation under load	60	%	EN 60811
permanent elongation	0	%	
Hot Pressure Test at 125°C/K=1, max. penetration	< 50	%	EN 60811
Bending Test at -40°C	no cracks		EN 60811
<b>Ageing</b>			
Mechanical properties after ageing in Air Oven, 135°C/168 hours			
change in Tensile Strength	+1	%	EN 60811
change in Tensile Elongation	-10	%	

	nominal value	unit	test method
<b>Ageing</b>			
Mechanical properties after ageing in Air Bomb, 0.55 MPa, 127°C/40 hours			
change in Tensile Strength	-8	%	EN 60811
change in Tensile Elongation	+11	%	
<b>Chemical resistance</b>			
IRM 902 Oil Immersion Test, 100°C/168 hours			
change in Tensile Strength	-18	%	EN 60811
change in Tensile Elongation	-22	%	
IRM 903 Oil Immersion Test, 70°C/168 hours			
change in Tensile Strength	-24	%	EN 60811
change in Tensile Elongation	-26	%	
1N NaOH Solution Immersion Test, 23°C/168 hours			
change in Tensile Strength	-27	%	EN 60811
change in Tensile Elongation	-8	%	
1N Oxalic Acid Solution Immersion Test, 23°C/168 hours			
change in Tensile Strength	-12	%	EN 60811
change in Tensile Elongation	+20	%	
Environmental Stress Cracking Resistance			
Condition A, 50°C, 3.00 mm, 10% Igepal	> 1000	hours	ASTM D1693
<b>Burning properties</b>			
Limiting Oxygen Index	38	%	ASTM D2863
Temperature Index	300	°C	NES 715
<b>Burning properties</b>			
Calorific Potential, upper (gross)	15.5	MJ/kg	ISO 1716
Corrosive Gas in Smoke			
conductivity	< 2.5	µS/mm	IEC 60754-2
pH	> 4.3	-	
Halogenidric Acid Emission	< 0.1	%	IEC 60754-1

**Notes:**

<sup>(1)</sup> Typical properties are not to be construed as specification. Tests reported are performed on pressed or extruded specimens, added with 5% of Catalyst Masterbatch CT/2-OR UV and crosslinked in hot water at 95°C for 6 hours

<sup>(2)</sup> Test performed without Catalyst Masterbatch addition

## Additional information

The product must be stored under the following conditions:

- closed and undamaged bags
- ambient temperature not exceeding 30°C
- avoid direct exposure to sunlight and weathering

Product alterations could occur due to extended period of storage; shelf life: 6 months

Padanaplast S.r.l accepts no liability of any kind in case the above mentioned conditions are not fulfilled

Packaging

- 25 kg moisture-resistant bags on 1375 kg pallet

## Processing information

### Extruder temperature setting:

barrel zone 1	100 to 120 °C
barrel zone 2	110 to 130 °C
barrel zone 3	130 to 150 °C
barrel zone 4	140 to 150 °C
collar	140 to 150 °C
crosshead	150 to 160 °C
die	150 to 170 °C

### Extrusion notes:

Processing

Cogegum® GFR/380 pregrafted base must be added with Catalyst Masterbatch CT/2-OR UV at 5% by weight to promote curing. Other Catalyst Masterbatch grades can be used accordingly to information given in the specific technical literature. Blending must be done just before using (2-3 hours max.). Catalyst Masterbatch doesn't need any predrying if stored in dry conditions in the original closed bags; in case, predrying can be made at 50-60°C for 4-8 hours  
Cogegum® GFR grades are sensitive to moisture; open bags must be used within 4 hours. Cogegum® GFR grades must be not predried in any case.

Extrusion equipment

- standard extruders for thermoplastics equipped with barrier screw (1.4÷2.4 compression ratio and 25 L/D ratio) are suggested
- screw thermoregulation suggested at 120°C
- filter net: normally not necessary
- semi-tube tools are suggested; if tubing tools must be used D.D.R. should not exceed 1.5

Coloring

- EVA or PE based color masterbatches added at 1.2-1.5% by weight are suggested; in order to prevent precrosslinking during processing, color masterbatch should be predried (4-6 hours at 50-60°C)

### Curing

- by immersion in hot water at 60-70°C
- by exposure in ambient, crosslinking time depends on ambient temperature and relative humidity
- in all cases curing time depends on insulation thickness; for 0.7-1.2 mm wall thickness 3-6 hours are generally necessary in case of force curing in hot water

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Padanaplast S.r.l. nor any of its affiliates makes any warranty, express or implied, including merchantability, fitness for use or accepts any liability in connection with this product, related information or its use. The use of this product is not subject to our direct control, therefore, the user alone must finally, under his own responsibility, determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The products are for use by technically skilled persons, with adequate training on how to use chemical products, at their own discretion and risk. The information provided does not relate to the use of this product in combination with any other substance or any other process. In no event Padanaplast S.r.l. will be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information.

Padanaplast S.r.l. makes no representation or warranty, express or implied, that the use of Information will not infringe any patent. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks belong to Finproject S.p.A., A Versalis (Eni) Company.

©Padanaplast S.r.l. 2022. All rights reserved.

[www.padanaplast.com](http://www.padanaplast.com)

[info@padanaplast.com](mailto:info@padanaplast.com)