

**Product description**

Elastomer based compound, moisture curable by addition of a catalyst masterbatch (Sioplas® method). This material complies with RoHS requirements.

Application: W&C insulation and sheathing

Standard complying

EN 50363-1 EI4 EI6 and EI7; EN 50363-2 EM3 and EM6; BS 7655 GP4, GP5, and GP7; EN 60092/360 EPR; Cenelec HD 603 DIH1; IEC 60502 EPR; VDE 0207/20 3GI3.

Availability

Africa & Middle East, Asia Pacific, Europe, Latin America, North America

Verify commercial availability and registration status in each country with local sales representative

Typical properties ⁽¹⁾	nominal value	unit	test method
Physical			
Density at 23°C	0.900	g/cm ³	ASTM D792
Melt Flow Index, 190°C/2.16 kg ⁽²⁾	0.70	g/10'	internal method
Water absorption 24h at 100°C	1.0	mg/cm ²	EN 60811
Hardness, Shore A	84	-	ISO 868
Hardness, Shore D	23	-	
Mechanical			
Tensile Strength at break	15.0	MPa	EN 60811
Tensile Elongation at break	500	%	
Tear Strength	8.0	kN/m	ASTM D1938
Thermal			
Hot Set Test at 200°C, 20 N/cm ²			
elongation under load	50	%	EN 60811
permanent elongation	0	%	
Hot Set Test at 250°C, 20 N/cm ²			
elongation under load	70	%	EN 60811
permanent elongation	0	%	
Ageing			
Mechanical properties after ageing in Air Oven, 100°C/336 hours			
change in Tensile Strength	+9	%	EN 60811
change in Tensile Elongation	+6	%	
Mechanical properties after ageing in Air Oven, 135°C/168 hours			
change in Tensile Strength	+3	%	EN 60811
change in Tensile Elongation	-4	%	
Mechanical properties after ageing in Air Bomb, 0.55 MPa, 127°C/40 hours			
change in Tensile Strength	-2	%	EN 60811
change in Tensile Elongation	-9	%	

	nominal value	unit	test method
Electrical			
Volume Resistivity at 20°C	4.1 E+15	Ω x cm	IEC 60502
Volume Resistivity at 90°C	2.7 E+14	Ω x cm	
Insulation Resistance Constant at 20°C	15000	MΩ x km	IEC 60502
Insulation Resistance Constant at 90°C	1000	MΩ x km	
Dielectric Strength	33	kV/mm	ASTM D149
Dielectric constant (1kHz)	2.3	-	ASTM D150
Dissipation Factor (1kHz)	1.0 E-3	-	ASTM D150

Notes:

⁽¹⁾ Typical properties are not to be construed as specification. Tests reported are performed on pressed or extruded specimens, added with 5% of Catalyst Masterbatch CT/1 and crosslinked in hot water at 95°C for 2 hours

⁽²⁾ Test performed without Catalyst Masterbatch addition

Additional information

The product must be stored under the following conditions:

- closed and undamaged bags
- ambient temperature not exceeding 30°C
- avoid direct exposure to sunlight and weathering

Product alterations could occur due to extended period of storage; shelf life: 9 months

Padanaplast S.r.l accepts no liability of any kind in case the above mentioned conditions are not fulfilled

Packaging

- 25 kg moisture-resistant bags on 1375 kg pallet

Processing information

Extruder temperature setting:

barrel zone 1	120 to 140 °C
barrel zone 2	120 to 150 °C
barrel zone 3	130 to 160 °C
barrel zone 4	140 to 170 °C
collar	140 to 170 °C
crosshead	140 to 170 °C
die	150 to 170 °C

Extrusion notes:

Processing

Polidiemme® G/400 pregrafted base must be added with Catalyst Masterbatch CT/1 at 5% by weight to promote curing. Other Catalyst Masterbatch grades can be used accordingly to information given in the specific technical literature. Blending must be done just before using (2-3 hours max.). Catalyst Masterbatch doesn't need any predrying if stored in dry conditions in the original closed bags; in case, predrying can be made at 50-60°C for 4-8 hours

Polidiemme® G grades are sensitive to moisture; open bags must be used within 4 hours. Polidiemme® G grades must be not predried in any case.

Extrusion equipment

- standard PVC extruders with single or double flight screw (20 to 30 L/D ratio) are suggested.
- don't use screw thermoregulation
- filter net: normally not necessary
- compression or semi-compression tools are suggested

Coloring

- EVA or PE based color masterbatches added at 0.6-1.0% by weight are suggested; in order to prevent precrosslinking during processing, colour masterbatch should be predried (4-6 hours at 50-60°C)

Curing

- by immersion in hot water at 60-70°C
- by exposure in ambient, crosslinking time depends on ambient temperature and relative humidity
- in all cases curing time depends on insulation thickness; for 0.7-1.2 mm wall thickness 3-6 hours are generally necessary in case of force curing in hot water

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Padanaplast S.r.l. nor any of its affiliates makes any warranty, express or implied, including merchantability, fitness for use or accepts any liability in connection with this product, related information or its use. The use of this product is not subject to our direct control, therefore, the user alone must finally, under his own responsibility, determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The products are for use by technically skilled persons, with adequate training on how to use chemical products, at their own discretion and risk. The information provided does not relate to the use of this product in combination with any other substance or any other process. In no event Padanaplast S.r.l. will be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information.

Padanaplast S.r.l. makes no representation or warranty, express or implied, that the use of Information will not infringe any patent. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks belong to Finproject S.p.A., A Versalis (Eni) Company.

©Padanaplast S.r.l. 2022. All rights reserved.

www.padanaplast.com

info@padanaplast.com